

PHYSICAL & STAINING TESTS (One hour covered spot)

Sulfuric Acid 50%	No visual effect
Combustion cc naphtha ignited	No visual effect
Belmar Scrape Adhesion	Pass 4 kg
Hoffman Scratch	Pass 800g
Impact-2 lbs bevel steel rod 8" drop	No cracks in film
Abrasion Resistance	CS-17 wheels 900 cycles
Humidity-24 hours @120 degF	
96% +/- 2% Relative Humidity	No visual effect
Vinegar	No visual effect
Lemon Juice	No visual effect
Grape Juice	No visual effect
Ketchup	No visual effect
Coffee	No visual effect
Olive Oil	No visual effect
100 Proof Alcohol	No visual effect
Nail Polish Remover	No visual effect
Lacquer Thinner	No visual effect

NOTE: These are not for our Kinon metal products. Metal products will behave as per their specific metal.